

HAVEL COMPOSITES CZ s.r.o. Svésedlice 67

783 54 Přáslavice tel.: +420 585 129 011 fax: +420 585 129 040

info@havel-composites.com www.havel-composites.com

IČ: 25907379 DIČ: CZ25907379

AEROGLASS GLASS FABRICS

Weave	Density (ends/cm) 0º(Warp) 90º(Weft)		Yarn (Tex) 0º(Warp) 90º(Weft)		Fabric Width(mm)	Fabric Weight	Standard Weight (GSM)			Tensile Strength (N/25mm) 09(Warp) 909(Weft)		Moisture Content (%)	Loss on Ignition
		(/	, ,,	, ,		(GSM)	(0	JOIVI			, ,	(70)	(%)
Plain	16	15	33	33	1000	110	110	±	10	400	400	0-0.2	0.3-0.8
Twill	16	15	33	33	1000	110	110	±	10	400	400	0-0.2	0.3-0.8
Twill	16	13	66	66	1000	200	200	±	20	900	700	0-0.2	0.3-0.8
Plain	8	7	99	99	1000	140	140	±	11	600	600	0-0.2	0.3-0.8
Plain	12	12	66	66	1000	160	160	±	12	700	650	0-0.2	0.3-0.8
Twill	12	12	66	66	1000	160	160	±	12	700	650	0-0.2	0.3-0.8
Plain	8	7	132	132	1000	200	200	±	16	650	550	0-0.2	0.3-0.8
Plain	6	5	200	200	1000	220	220	±	18	650	550	0-0.2	0.3-0.8
Plain	8	7	200	200	1000	280	280	±	24	1000	800	0-0.2	0.3-0.8
Twill	8	7	200	200	1000	280	280	±	24	1000	800	0-0.2	0.3-0.8
Plain	8	7	264	264	1000	390	390	±	32	1200	1100	0-0.2	0.3-0.8
Twill	8	7	264	264	1000	390	390	±	32	1200	1100	0-0.2	0.3-0.8
Twill	6	6	330	330	1000	390	390	±	32	1200	1100	0-0.2	0.3-0.8
Plain	2.9	2.9	600	600	1000	350	350	±	28	2200	2000	0-0.2	0.3-0.8
Plain	3.2	4	600	600	1000	450	450	±	36	2700	2400	0-0.2	0.3-0.8

Note for the reader

Havel Composites CZ s.r.o. (Havel) was convinced of the accuracy of the information provided at the time this material was prepared, or the information was taken from sources that the company believed to be reliable; however, the user is responsible for studying and understanding other relevant sources of information in such a way as to comply with all laws and procedures applicable to the safe handling and handling of the product and to determine the suitability of the product for its intended use. For all products supplied by Havel, Havel's sales terms and conditions apply. THE COMPANY MAKES NO WARRANTY, WHETHER EXPRESS OR IMPLIED, TO ANY PRODUCT OR ITS MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. HAVEL MAKES NO WARRANTY CONCERNING THE ACCURACY OF ANY INFORMATION CONTAINED BY HAVEL, except that its products will be in conformity with Havel's technical specifications. The information provided here does not constitute an offer for the sale of any product.

Zpracoval: Ing. Richard Moravec Dne: 1.3.2019